


Roofing & Waterproofing

PRODUCT SELECTOR



FLAT & TAPERED - EPS

APPLICATION : All roofing & re-roofing, In house Taper design available.
Save time and money with factory cut crickets and skylights.
*CHARACTERISTICS** : Thickness - 1/8" to 52" Compressive Strength 10-60 PSI




FANFOLD UNDERLAYMENT & PROTECTION BOARD

APPLICATION : For recover over existing roof systems without the use of a slip sheet
*CHARACTERISTICS** : Thickness - 3/8", 1/2", 3/4", comes in 200 sq. ft. bundles
Compressive strength 10-60 PSI..




HOLEY BOARD

APPLICATION : For use in lightweight concrete systems
*CHARACTERISTICS** : 2'x4', 2'x8', 4'x4', & 4'x8' boards. Thickness - 3/4" to 52"
Compressive strength 10-60 PSI..



StarRGard

APPLICATION : Commonly used in place of XPS & PolyISO in residential and commercial construction.
*CHARACTERISTICS** : Thickness - 1/2"-11". Metallic, clear or white faces.
Compressive strength 10-60 PSI.



FLUTEFILL

APPLICATION : Used as a filler in recover applications of existing metal roof profiles.
*CHARACTERISTICS** : Taper, straight, or custom- cut profiles. Available in single panel widths or can be cut into 48" to 120" lengths. Compressive strength 10-60 PSI.



PLANT LOCATIONS

ARLINGTON

3220 EAST AVENUE F
ARLINGTON, TX 76011

800-722-6218

ANTHONY

1004 OMAR ROAD
ANTHONY, TX 79821

915-886-4636

KINGMAN

4445 OLYMPIC WAY
KINGMAN, AZ 86401

928-681-2800





Roofing & Waterproofing

PRODUCT SELECTOR

StarRfoam Roof Insulation R-Value

ASTM C 578	TYPE I	TYPE VIII	TYPE II	TYPE IX	TYPE XIV	TYPE XV
PSI	10	15	20	25	40	60
R-Value	3.86*	4.11*	4.29*	4.76*	4.8*	4.9*
R-1	0.3"	0.2"	0.2"	0.2"	0.2"	0.2"
R-2	0.5"	0.5"	0.5"	0.4"	0.4"	0.4"
R-3	0.8"	0.7"	0.7"	0.6"	0.6"	0.6"
R-4	1.0"	1.0"	0.9"	0.8"	0.8"	0.8"
R-5	1.3"	1.2"	1.2"	1.1"	1.0"	1.0"
R-6	1.6"	1.5"	1.4"	1.3"	1.3"	1.2"
R-7	1.8"	1.7"	1.6"	1.5"	1.5"	1.4"
R-8	2.1"	1.9"	1.9"	1.7"	1.7"	1.6"
R-9	2.3"	2.2"	2.1"	1.9"	1.9"	1.8"
R-10	2.6"	2.4"	2.3"	2.1"	2.1"	2.0"
R-11	2.8"	2.7"	2.6"	2.3"	2.3"	2.2"
R-12	3.1"	2.9"	2.8"	2.5"	2.5"	2.4"
R-13	3.4"	3.2"	3.0"	2.7"	2.7"	2.7"
R-14	3.6"	3.4"	3.3"	2.9"	2.9"	2.9"
R-15	3.9"	3.6"	3.5"	3.2"	3.1"	3.1"
R-16	4.1"	3.9"	3.7"	3.4"	3.3"	3.3"
R-17	4.4"	4.1"	4.0"	3.6"	3.5"	3.5"
R-18	4.7"	4.4"	4.2"	3.8"	3.8"	3.7"
R-19	4.9"	4.6"	4.4"	4.0"	4.0"	3.9"
R-20	5.2"	4.9"	4.7"	4.2"	4.2"	4.1"
R-21	5.4"	5.1"	4.9"	4.4"	4.4"	4.3"
R-22	5.7"	5.4"	5.1"	4.6"	4.6"	4.5"
R-23	6.0"	5.6"	5.4"	4.8"	4.8"	4.7"
R-24	6.2"	5.8"	5.6"	5.0"	5.0"	4.9"
R-25	6.5"	6.1"	5.8"	5.3"	5.2"	5.1"
R-26	6.7"	6.3"	6.1"	5.5"	5.4"	5.3"
R-27	7.0"	6.6"	6.3"	5.7"	5.6"	5.5"
R-28	7.3"	6.8"	6.5"	5.9"	5.8"	5.7"
R-29	7.5"	7.1"	6.8"	6.1"	6.0"	5.9"
R-30	7.8"	7.3"	7.0"	6.3"	6.3"	6.1"
R-35	9.1"	8.5"	8.2"	7.4"	7.3"	7.1"
R-38	9.8"	9.2"	8.9"	8.0"	7.9"	7.8"
R-40	10.4"	9.7"	9.3"	8.4"	8.3"	8.2"

*Per ASTM-C-578 tolerances are +/- 1/16" on thickness

R-Values and Thicknesses @75 F